

Product Presentation



Application

Determine the thickness reduced value and hardness decreased value of porous elastic materials used in interior decoration.

Theory

Put a square sample on the lower platform, and Repeatedly recess the sample by an indenter, whose size is smaller than the specimen.

Reach the max.load under a certain range during each impact period, and then evaluate the sample performance after a certain times.

Standards

GB/T 18941,GB/T 12825,ISO 3385

Key Specification

Test speed	70±5 r/min
Test Times	0~999999 times, setttable.
Upper Platen	Diameter: Φ250mm Fillet of lower edge: R25mm
Stroke	80mm
Sample load	750±20N
Dimension (specimen)	(380±20)x(380±20)x(50±2)mm
Counting	0~999 999 times
Size(W*D*H)	69x50x115cm
Weight	About 150kg
Power	1 φ , AC 220V 50Hz